## Fabric Selection Guide



## High Performance Architectural Fabrics

			3820 Type I	8424 Type I	8028 Type II	9032 Type III
Base Fabric Type Base Fabric Weight (nominal)			Polyester 5.0 oz/yd <sup>2</sup>	Polyester 5.0 oz/yd <sup>2</sup>	Polyester 7.5 oz/yd <sup>2</sup>	Polyester 10.0 oz/yd²
Finished Coated Weight ASTM D751			20.0 oz/yd² +2/-1 oz/yd²	24.0 oz/yd² +2/-1 oz/yd²	28.0 oz/yd² +2/-1 oz/yd²	32.0 oz/yd <sup>2</sup> +2/-1 oz/yd <sup>2</sup>
Trapezoid Tear ASTM D4533				50/60 lb	85/85 lb	100/100 lb
Grab Tensile ASTM D751			375/325 lb	375/350 lb	700/700 lb	840/840 lb
Strip Tensile ASTM D751 Procedure B			300/275 lb/in	300/275 lb/in	515/515 lb/in	650/650 lb/in
Adhesion ASTM D751 Dielectric Weld			10 lb/in	10 lb/in	10 lb/in	10 lb/in
Hydrostatic Resistance ASTM D751 Procedure A			500 psi	500 psi	500 psi	500 psi
Low Temperature ASTM D2136 1/8" mandrel, 4 hr	LTA	LTC	Pass @ -40° F 	Pass @ -40° F Pass @ -67° F	Pass @ -40° F Pass @ -67° F	Pass @ -40° F 
Flame Resistance	NFPA 701		Pass	Pass	Pass	Pass
	California Fire Marshal	I	Pass	Pass	Pass	Pass
	ASTM E84 Class A		Pass	Pass	Pass	
	ULC S102 & S109		Pass	Pass	Pass	ULC S109 only
Top Finish Systems			Acrylic, PVDF	Acrylic, PVDF, Kynar®, Tedlar®	Acrylic, PVDF, Kynar®, Tedlar®	Acrylic, PVDF, Kynar®, Tedlar®
Width (inches)			72 98	71	56 71 98	54 71

Unless stated otherwise, values presented above represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.





